## Patent Number(s): JP52129799-A

Title: Polyester prodn. esp. polyethylene terephthalate with fewer ether gps. - by esterification in presence of e.g. cobalt cpd. and then adding alkoxide of antimony and/or germanium and polycondensing

Patent Assignee Name(s) and Code(s): MITSUBISHI RAYON CO LTD (MITR-C)
Derwent Primary Accession Number: 1977-88840Y [50]

Patents Cited by Inventor: 0
Patents Cited by Examiner: 0
Patents Cited by Examiner: 0
Articles Cited by Examiner: 0
Articles Cited by Examiner: 0

Prodn. of polyester is by esterifying terephthalic acid and ethylene glycol in two steps, continuously followed by subjecting the esterified prod. to polycondensation.

Ethylene glycol and terephthalic acid are mixed in a molar ratio of 1.2-2.0 and the mixture is made into a slurry, which is continuously fed to a first reaction vessel a part of the ethylene glycol being taken out of the bottom of the rectification tower attached to the first reaction vessel so that the molar ratio f ethylene glycol and terephthalic acid in the reaction product in the first reaction vessel is 1.0-1.3. AT least part of the liquid thus removed is fed to the second reaction vessel together with the esterified product taken out of the first reaction vessel.

Esterification in the second reaction vessel is with a molar ratio ethylene glycol and terephthalic acid of 1.05-1.3. Esterification is conducted in the presence of 1 Co Mg or Ti pd. followed by addition of antimony alkoxide and/or germanium alkoxide and polycondensation.

Process allows prodn. of polyethylene terephthalate contg. fewer ether linkages and high whiteness.

International Patent Classification: C08G-063/22

Derwent Class: A23 (Polyamides, polyesters, polycarbonates, alkyds)
Derwent Manual Code(s): A02-A06; A02-A07; A02-A07A; A05-E04A

Patent Details:

 Patent Number
 Publ. Date
 Main IPC
 Week
 Page Count
 Language

 JP52129799-A
 31 Oct 1977
 197750
 197750

Priority Application Information and Date:

JP047444 | 26 Apr 1976